

Coherent phase slips in superconducting nanorings

D. Mozyrsky* and D. Solenov

Theoretical Division (T-4) and the Center for Nonlinear Studies (CNLS),
Los Alamos National Laboratory, Los Alamos, NM 87545, USA

(Dated: July 18, 2011)

We study quantum fluctuations of persistent current in a small superconducting ring. Based on a microscopic model of the ring we argue that under certain conditions such ring will exhibit coherent quantum phase slips, similar to those in a flux qubit. We evaluate the frequency of such coherent oscillations and find that it is strongly dependent on wire's diameter primarily due to the large momentum released by the condensate as a result of a phase slip event. We also find that the value of such frequency is not a self-averaging quantity, that is, it depends on a particular realization of the static impurity potential.

PACS numbers: 74.78.Na, 74.40.-n, 74.50.+r, 85.25.-j

Relaxation of persistent currents in quasi one-dimensional (1D) superfluids due to phase slip transitions has been a subject of extensive studies over several decades. While at finite temperatures phase slips are known to occur via thermal activation through an effective barrier [1], at sufficiently low temperatures they are believed to be generated by the quantum fluctuations of the order parameter, i.e., macroscopic quantum tunneling. Some experimental studies of electric transport in superconducting *wires* at low temperatures have, indeed, demonstrated finite residual resistivity in sufficiently thin wires [2, 3], consistent with the quantum phase slip (QPS) picture [4]. Other experimental studies [5], however, did not confirm these results, suggesting, in particular, that the experiments in Ref. [2] could be explained in terms of thermally activated phase slips in the presence of Coulomb blockade.

It has been argued in the literature [6, 7] that the controversy (of whether the observed phase slips are of quantum origin) can be clarified by observing the coherent effects in fluctuations of electric currents, - the thermally activated phase slips, obviously, are not supposed to exhibit any phase coherence. In particular, based on *phenomenological* arguments, it was proposed that short and thin superconducting filaments can possibly operate as sources of *coherent* QPSs [6–8], just like Josephson junctions in flux qubits. The experimental evidence for coherent QPS in Josephson junction arrays has recently been reported in Ref. [9]. Yet, no *microscopic* theory of coherent QPS-driven current fluctuations has been developed so far.

In this paper we provide a microscopic theory of coherent QPS in a small superconducting (nano) ring. We argue that if a half-quantum of external magnetic flux is applied to the ring, it will exhibit coherent switching between states with different persistent currents, i.e., coherent QPS transitions. The rate (frequency) of such QPS is controlled by the strength of the impurity potential: For a translationally invariant system, i.e., in the “clean” limit, the QPS are suppressed due to the Landau

criterion [10, 11]. Indeed, a QPS event is accompanied by the production of sufficiently large momentum, which (at zero temperature) cannot be absorbed by the quasiparticles unless the current (or superfluid velocity) exceeds its critical value. In the presence of impurities the momentum conservation is “violated” and so the QPS can occur. However, as we show in this paper, the rate of the QPS is proportional to the Born's scattering cross-section of the condensate at the impurities, which is small for large QPS momenta, i.e., for wires whose diameter significantly exceeds the interparticle distance. Moreover, the value of the QPS frequency turns out to be strongly sample dependent: the ratio of its root-mean-square deviations to its average value is a constant which does not decrease with system's size, as in the case of incoherent QPS in sufficiently long wires [10, 12].

Before proceeding to the evaluation of the QPS frequency for a BCS superconductor, let us evaluate this quantity in the framework of the Bose-Luttinger liquid. The calculation for this model is rather straightforward and serves as a reference point for the more complex superconducting case. The Hamiltonian for such quantum liquid confined to a 1D ring with finite circumference L can be written as $H = H_0 + H_1$ [13], where

$$H_0 = H_Q + H_J = \sum_{k \neq 0} \omega_k a_k^\dagger a_k + (E_J/2)(\hat{J} - J_0)^2 \quad (1)$$

is the Hamiltonian of the liquid in the absence of impurity potential, i.e., for a translationally invariant system, and H_1 is due to the impurity potential. In Eq. (1) ω_k is energy of a quasiparticle with momentum $2\pi k/L$ and $a_k^\dagger$ (a_k) are bosonic operators that create (annihilate) the quasiparticles. The H_J term in Eq. (1) is the energy associated with the superfluid motion of the liquid and is characterized in terms of winding numbers $J = 0, \pm 1, \dots$, i.e., eigenvalues of operator $\hat{J}$. Constant E_J is related to the effective inductance of the liquid (typically of kinetic origin for both neutral systems and ultrathin superconducting wires) and J_0 is the “external” winding number supplied by the magnetic field (for charged particles) or

by the rotation (for neutral particles). Note that in Eq. (1) the states with different J 's are decoupled from each other owing to the Landau criterion.

The presence of $H_1 = \int_0^L dx V(x)n(x)$, where $V(x)$ is impurity potential and n is 1D particle density, introduces a matrix element between states with different J 's. This can be seen by writing n in terms of the displacement phase Θ [13] according to the relation $n = n_0 + \delta n$,

$$\delta n \sim \sum_{l>0} (\hat{J}^-)^l \exp(il\Theta) + (\hat{J}^+)^l \exp(-il\Theta), \quad (2)$$

$$\Theta = 2\pi n_0 x + \sum_{k \neq 0} \left(\frac{2\pi c \alpha}{L \omega_k} \right)^{1/2} (a_k^\dagger + a_{-k}) e^{2\pi i k x / L},$$

where operators $\hat{J}^\pm$ raise/lower the winding numbers J by ± 1 , and α is the Tonks parameter, $\alpha = \pi n_0 / (mc)$, m is particle's mass and c is sound velocity. In this paper we set both the Planck constant and the speed of light equal to 1. The value of $\langle 0 | H_1 | 1 \rangle$, where $|0\rangle$ and $|1\rangle$ are the states of the liquid with zero and one winding numbers and zero quasiparticles, can now be easily evaluated with the use of Eq. (2). Retaining $l = 1$ terms only in Eq. (2), we obtain

$$\langle 0 | H_1 | 1 \rangle \sim \left(\int_0^L dx V(x) e^{2\pi i n_0 x} \right) e^{-\frac{\pi c \alpha}{L} \sum_{k \neq 0} \frac{1}{\omega_k}}. \quad (3)$$

If the value of this matrix element is small compared to the gap between different quasiparticle states $\Delta\omega = 2\pi c/L$, the system's dynamics at low enough temperatures (i.e., for $T \ll \Delta\omega$) reduces to the transitions between $J = 0$ and $J = 1$ "ground" states (here and in the following we are interested in the degenerate $J_0 = 1/2$ case, which can always be achieved by the appropriate choice of magnetic field or rotation frequency). That is, if the system is initially set in a state with, say, $J = 0$, its probability to occupy that state, $|\langle 0(t) | 0(0) \rangle|^2$, will exhibit coherent oscillations with frequency $\omega_0 = |\langle 0 | H_1 | 1 \rangle|$, as in the case of a two-state system. Assuming the Bogolubov's dispersion relation $\omega_k = c[(2\pi k/L)^2 + (2\pi k/L)^4 \xi^2/4]^{1/2}$, where $\xi = (mc)^{-1}$ is coherence length, we obtain that $\sum_n \omega_n^{-1} \simeq \ln(2e^{1/2}L/\pi\xi)$ in Eq. (3) and

$$\omega_0 \sim |V_{n_0}| \times (\pi\xi/2e^{1/2}L)^\alpha, \quad (4)$$

where $V_{n_0} = \int dx V(x) e^{2\pi i n_0 x}$. It is interesting that ω_0 does not self-average with the growth of L . Indeed, if we assume that the disorder potential is short range and Gaussian with $\langle V(x)V(x') \rangle = V_0^2 \delta(x - x')$, we see that the average frequency $\langle \omega_0 \rangle = (\pi^{1/2}/2)n_0 V_0 L^{1/2} (\pi\xi/2e^{1/2}L)^\alpha$, while its root-mean-square deviations $(\langle \Delta\omega_0^2 \rangle)^{1/2} \sim \langle \omega_0 \rangle$. Therefore we predict that the frequency of coherent oscillations is strongly sample-dependent. While this fact may seem surprising, it is a direct consequence of systems's coherence: Indeed,

for a sufficiently large system, e.g., Refs. [10, 12], phase slips occur at different, disconnected from each other regions, which effectively leads to self-averaging. In our case the phase slips are strongly overlapping (note that $\omega_0 \ll c/L$) and thus averaging over the disorder does not occur.

Let us now consider the fermionic model. The Hamiltonian density for electrons within the standard BCS model can be written as

$$H = \frac{1}{2m} \psi_\sigma^\dagger (i\nabla - e\mathbf{A}_0)^2 \psi_\sigma + V(\mathbf{r}) \psi_\sigma^\dagger \psi_\sigma + e^2 \int d^3\mathbf{r} \frac{\psi_\sigma^\dagger(\mathbf{r}) \psi_\sigma(\mathbf{r}) \psi_{\sigma'}^\dagger(\mathbf{r}') \psi_{\sigma'}(\mathbf{r}')}{|\mathbf{r} - \mathbf{r}'|} + (\Delta\psi_\uparrow\psi_\downarrow + \text{h.c.}), \quad (5)$$

where repeated index σ means summation over $\uparrow$ and $\downarrow$ spin components of fermionic field $\psi_\sigma(\mathbf{r})$. In Eq. (5) $\mathbf{A}_0$ is vector potential due to an external magnetic field and $V(\mathbf{r})$ is impurity potential, to be specified below. The electrons are restricted to move in a wire of cross section $S_0 = \pi r_0^2$ (r_0 is assumed to be much smaller than the superconducting coherence length ξ_s), which has the shape of a ring (or torus) with circumference length $L \gg \xi_s$. We assume that the magnitude of the superconducting order parameter $\Delta(\mathbf{r}) = |\Delta_0| e^{i\theta(\mathbf{r})}$ is fixed and allow for variations of its "soft" phase θ only. Such assumption is justified by the existence of the gapless (i.e., sound-like) mode arising in a quasi-1D situation (see below). In Eq. (5) we neglect the geometric inductance of the loop, which is small compared to the kinetic inductance for ultrathin wires.

Unfortunately it does not seem possible to directly introduce the displacement phase Θ for the Cooper pairs as it was done in the previous model. For the conventional phase θ , however, one can derive an effective low energy action within the perturbative approach, i.e., assuming that gradients of θ as well as its time derivatives are small. In order to do so we apply a gauge transformation $\psi_\sigma \rightarrow \psi_\sigma e^{i\theta/2}$ to the Hamiltonian in Eq. (5) and expand the corresponding action in terms of $\partial_\tau \theta$ and $\nabla \theta$.

The first order contribution to the effective action for the phase θ is the Berry phase term [14]

$$\mathcal{S}_1 = i \int d\tau d^3\mathbf{r} \langle \psi_\sigma^\dagger(\mathbf{r}) \psi_\sigma(\mathbf{r}) \rangle \partial_\tau \theta. \quad (6)$$

In Eq. (6) the averaging is taken with respect to the ground state of the electrons, but *not* with respect to the disorder potential V . The importance of particle density variations has been discussed in Refs. [10, 11], where it was shown that the QPS processes are suppressed by the Berry phase, e.g., Eq. (6), in translationally invariant systems. Such suppression is, essentially, a consequence of Landau criterion, discussed above. Note that the quantity $\int d\tau \partial_\tau \theta$ is a topological invariant: It is determined by a discrete set of points corresponding to the positions of the QPS rather than by the particular dependence of θ on τ and $\mathbf{r}$; see below.

The second order terms in $\partial_\tau \theta$ and $\nabla \theta$ have been derived in Refs. [4]. For consistency we briefly outline the calculation. First one introduces the scalar potential ϕ by decoupling the Coulomb interaction term in Eq. (5) via Hubbard-Stratonovich transformation. The second order terms obtained after the averaging over the ψ fields are

$$\mathcal{S}_2 = \int d\tau d^3\mathbf{r} \left[\nu(i\partial_\tau \theta + 2e\phi)^2 + (\rho_s/2m)(\nabla\theta + 2e\mathbf{A}_0)^2 + (\nabla\phi)^2/8\pi \right], \quad (7)$$

where ν is free electron density of states and ρ_s is the density of superconducting electrons. Note that Eq. (7) is also averaged with respect to the impurity potential. Such averaging is valid since θ is a slowly varying quantity. Moreover, since the thickness of the wire is small compared to the superconducting coherence length, θ is effectively a 1D field. The field ϕ can now be excluded from Eq. (7). In doing so one should keep in mind that ϕ is also nonzero in the region outside the wire. The contribution of the outside region can be shown to dominate over the inside region and the last term in Eq. (7) can be written as $\int dx C \phi^2/2$, where $C \simeq \epsilon[2\ln(L/r_0)]^{-1}$ is the capacitance (per unit length) of the ring, ϵ is dielectric constant of the surrounding medium and the scalar potential ϕ inside the wire is assumed to be constant along the wire's cross section. Then ϕ can be integrated out and from Eqs. (6, 7) we obtain an effective Lagrangian density for $\theta(\tau, x)$:

$$\mathcal{L} = in(x)\partial_\tau \theta + \frac{C}{2e^2}(\partial_\tau \theta)^2 + \frac{\rho_s S_0}{2m}(\partial_x \theta + 2eA_0)^2. \quad (8)$$

In Eq. (8) we have defined the 1D density $n(x) = \int d^2\mathbf{r}_\perp \rho(\mathbf{r})$, where $\rho(\mathbf{r}) = \langle \psi_\sigma^\dagger(\mathbf{r})\psi_\sigma(\mathbf{r}) \rangle$, and assumed that $e^2\nu S_0 \gg C$. A_0 in the last term in Eq. (8) is the component of the external vector potential $\mathbf{A}_0$ along the direction of the wire. The last two terms in Eq. (8) describe the Mooij-Schon gapless plasmon mode propagating with phase velocity $c_s = (\rho_s S_0 e^2/mC)^{1/2}$ [4].

We are interested in the probability amplitude for the system to remain in state $|0\rangle$, i.e., with zero current. If a half of magnetic flux, $\Phi_0 = \int dSB_0 = \oint d\mathbf{x} \mathbf{A}_0$, is applied, i.e., $\Phi_0 \rightarrow \pi/2e$, the zero current state is degenerate with the state with one winding number, $|1\rangle$, i.e., with electric current equal to $2\pi e\rho_s/mL$. The amplitude $\langle 0(\tau)|0(0) \rangle$ can be evaluated using instanton method. The leading contribution is

$$\langle 0(\tau)|0(0) \rangle \sim 1 + K \int_0^\tau d\tau_1 \int_0^{\tau_1} d\tau_2 \times \int_0^L dx_1 \int_0^L dx_2 e^{-\mathcal{S}_{cl}(\tau_1, x_1; \tau_2, x_2)} + \dots, \quad (9)$$

where action $\mathcal{S}_{cl}$ is evaluated along the classical trajectory, which starts in state $|0\rangle$, then, at time τ_1 passes on to the state $|1\rangle$, and at time τ_2 returns to $|0\rangle$. The

coefficient K is related to the determinant for the fluctuations around the classical trajectory. It is independent of the first, topological term in Eq. (8), and was estimated in Refs. [11]: $K \sim \alpha_s^2/(\xi_s^2\tau_0^2)$, where $\tau_0 = \xi_s/c_s$ and $\alpha_s = \pi(\rho_s S_0 C/e^2 m)^{1/2}$.

The classical trajectory action in Eq. (9) corresponds to a superposition of two phase slips (i.e., vortex at τ_1, x_1 and anti-vortex at τ_2, x_2) [4]. For a finite ring we should account for the boundary conditions: The system is periodic in x direction (with period L) and infinite along the τ direction (again we consider a zero temperature case). The (anti)vortex solutions for the phase θ satisfying such boundary conditions has the form

$$\theta(x, \tau) = \pm \text{sgn}(\tau - \tau_{1(2)}) \times \tan^{-1} \frac{e^{-2\pi c_s |\tau - \tau_{1(2)}|/L} \sin[2\pi(x - x_{1(2)})/L]}{1 - e^{-2\pi c_s |\tau - \tau_{1(2)}|/L} \cos[2\pi(x - x_{1(2)})/L]} \quad (10)$$

Note that in the limit $L \rightarrow \infty$ we recover the well known expression $\theta(x, \tau) \rightarrow \pm \tan^{-1}[(x - x_1)/c_s(\tau - \tau_1)]$, e. g., Refs. [4]. Using this solution and Eq. (8) we evaluate $\mathcal{S}_{cl}$ in Eq. (9). After some calculation we find

$$\mathcal{S}_{cl} = 2\pi i \int_{x_2}^{x_1} dx n(x) + \eta \Delta\Phi \Delta\tau + 2\alpha_s \ln(L/\xi_s) - 2\alpha_s \ln \left(1 + e^{-\frac{4\pi c_s |\Delta\tau|}{L}} - 2e^{-\frac{2\pi c_s |\Delta\tau|}{L}} \cos \frac{2\pi \Delta x}{L} \right), \quad (11)$$

where $\Delta\tau = \tau_2 - \tau_1$, $\Delta x = x_2 - x_1$, $\eta = 4\pi e\rho_s S_0/mL$ and $\Delta\Phi = \Phi_0 - \pi/2e$. The first term in Eq. (11) is due to the Berry phase in Eqs. (6, 8); it is controlled by the relative position of the vortices, but not by their internal structure. The second term in Eq. (11) is proportional to the bias energy $\eta\Delta\Phi$, i.e., the energy difference between states with and without current. The last two terms are the the vortex self-energy and interaction energy respectively.

At the point of degeneracy (for $\Delta\Phi = 0$), the interaction energy between vortices vanishes when $\Delta\tau = \infty$. Then the last term in the rhs of Eq. (9) is equal to $\omega_0^2 \tau^2/2$, where

$$\omega_0 = K^{1/2} e^{-\alpha_s \ln(L/\xi_s)} \left| \int_0^L dx' e^{2\pi i \int_0^{x'} dx n(x)} \right|. \quad (12)$$

Moreover, it is straightforward to verify that the next, four-vortex contribution in Eq. (9) is $\sim (\omega_0 \tau)^4/4!$, etc., and therefore $\langle 0(t)|0(0) \rangle = \cos(\omega_0 t)$, i.e., the system exhibits coherent oscillations with frequency ω_0 .

For a translationally invariant system (with $V = 0$), $n(x) = \text{const}$ and therefore the integral over x' in Eq. (12) vanishes and $\omega_0 = 0$, as expected. For not too strong disorder and not too thin wires we may write $n(x) = n_0 + \delta n(x)$, with $n_0 \gg \delta n$. Then

$$\int_0^L dx' e^{2\pi i [n_0 x' + \int_0^{x'} dx \delta n(x)]} \simeq \frac{1}{2\pi n_0} \int d^3\mathbf{r} e^{2\pi i n_0 x} \delta\rho(\mathbf{r}),$$

where $\rho(\mathbf{r}) = \rho_0 + \delta\rho(\mathbf{r})$. Since $\delta\rho(\mathbf{r}) \simeq \int d^3\mathbf{r}' \chi(\mathbf{r} - \mathbf{r}') V(\mathbf{r}')$, where χ is the static electronic susceptibility, Eq. (12) is basically equivalent to that for the bosonic model, e.g., Eqs. (3, 4). Note that the vortex self-interaction term $-\alpha_s \ln(L/\xi_s)$ in Eqs. (11, 12) coincides with the last exponent ($\sim \sum_n \omega_n^{-1}$) in Eq. (3), arising from the evaluation of $\langle \exp(i\Theta) \rangle$ in the bosonic problem.

Again, as in the bosonic problem, we expect that the QPS frequency is strongly sample-dependent, i.e., it is a random number whose average is comparable to its root-mean-square deviations. In order to estimate the typical (average) frequency of QPS oscillations, we must evaluate $\langle |\int dx e^{2\pi i n_0 x} \delta n(x)|^2 \rangle$. We assume that the disorder is due to random impurities carrying charge e , i.e., $V(\mathbf{r}) = \sum_{i=1}^{N_i} e^2/|\mathbf{r} - \mathbf{r}_i|$. The response function χ for the Hamiltonian in Eq. (5) is generally not well known at finite wavevectors. However, the momentum $2\pi n_0 = 2\pi\rho_0 S_0$ transferred from the condensate to the impurities as a result of a QPS event is rather high compared to both the Fermi wavevector k_F and the inverse screening radius. At such high momenta the electronic response function is that of free electrons, $\chi(q) \simeq \chi_0^{q \rightarrow \infty}(q) \simeq -4mk_F^3/(3\pi^2 q^2)$, and therefore

$$\langle |\int d^3\mathbf{r} e^{2\pi i n_0 x} \delta\rho(\mathbf{r})|^2 \rangle = [\chi_0^\infty (2\pi n_0) e^2 / \pi n_0^2]^2 N_i, \quad (13)$$

where N_i is the total number of impurities in the sample. The right hand side of Eq. (13) is $\sim S_0^8$ and therefore the QPS rates are strongly suppressed in wires, whose diameter significantly exceeds the Fermi wavelength.

Then we obtain an estimate for the average frequency:

$$\langle \omega_0 \rangle \sim \frac{\alpha_s^2 c_s N_i^{1/2}}{\xi_s^2 a_B \rho_0^4 S_0^5} \times \left(\frac{\xi_s}{L} \right)^{\alpha_s}, \quad (14)$$

where a_B is Bohr radius. Let us estimate the value of $\langle \omega_0 \rangle$ for typical experimental parameters. We consider a *MoGe* wire, e.g. Ref. [2], of diameter $2r_0 = 5\text{ nm}$ and length $L = 1\text{ }\mu\text{m}$. The density of conduction electrons ρ_0 can be estimated from the data on conductivity in the normal state, e.g. Ref. [15], $\sigma = e^2 \rho_0 / k_F l$. For an amorphous material, such as *MoGe*, the mean free path is of the order of interatomic distance $l \sim 4\text{ }\text{\AA}$, e.g. Ref. [15], and thus we obtain $\rho_0 \simeq 10^{28}\text{ m}^{-3}$. In order to estimate α_s and c_s we need values of ρ_s and C . Assuming that the wire is covered by a dielectric material, e.g. Ref. [2, 3, 5], we estimate that $C \sim 1$. The density of superconducting electrons is related to the normal electron density as $\rho_s \simeq \rho_0 (l/\xi_s)^2$ [16]. Taking $\xi_s = 8\text{ nm}$, e.g. Refs. [2, 15], we obtain $\rho_s \simeq 10^{25}\text{ m}^{-3}$ and $\alpha_s \simeq 0.5$ and $c_s \simeq 7 \times 10^5\text{ m/s}$. Finally, the number of impurities N_i is of the order of the total number of atoms in the wire and so we take $N_i \simeq 3 \times 10^5$. With such parameters we obtain $\langle \omega_0 \rangle \sim 10^3\text{ s}^{-1}$. As we pointed out above, the QPS rate is significantly suppressed by the small “scattering amplitude”, e.g. Eq. (13), due to the high value of the

QPS momentum. The value of $\langle \omega_0 \rangle$ can greatly increase in thinner wires, e.g. Eq. (14): For wires with diameter 2 nm we obtain $\langle \omega_0 \rangle \sim 10^7\text{ s}^{-1}$. The coherent QPS in such wires can presumably be detected by inductively coupling the ring to a SQUID.

In summary we have studied a possibility for generation of coherent QPS in small superconducting rings. We have evaluated the frequency of such transitions and found that it is appreciable only in ultrathin wires, i.e., with diameters not too strongly exceeding the electron’s Fermi wavelength. We have also shown that such frequency is a non-self-averaging, sample-dependent quantity.

We thank M. Boshier, I. Martin, S. D. Snyder and E. Timmermans for valuable discussions and comments. The work is supported by the US DOE.

* Electronic address: mozyrsky@lanl.gov

- [1] J. S. Langer and V. Ambegaokar, Phys. Rev. **164**, 498 (1967); D. E. McCumber and B. I. Halperin, Phys. Rev. B **1**, 1054 (1970).
- [2] A. Bezryadin, C. N. Lau, and M. Tinkam, Nature (London) **404**, 971 (2000); C. N. Lau, N. Markovic, M. Bockrath, A. Bezryadin, M. Tinkam, Phys. Rev. Lett. **87**, 217003 (2001).
- [3] F. Atomare, A. M. Chang, M. R. Melloch, Y. Hong and C. W. Tu, Phys. Rev. Lett. **97**, 017001 (2006).
- [4] A. D. Zaikin, D. S. Golubev, A. van Otterlo, G. T. Zimanyi, Phys. Rev. Lett. **78**, 1552 (1997); D. S. Golubev and A. D. Zaikin, Phys. Rev. B **64**, 014504 (2001).
- [5] A. Rogachev and A. Bezryadin, Appl. Phys. Lett. **83**, 512 (2003); A. Rogachev, A. T. Bollinger and A. Bezryadin, Phys. Rev. Lett. **94**, 017004 (2005); A. T. Bollinger, A. Rogachev and A. Bezryadin, Europhys. Lett. **76**, 505 (2006).
- [6] J. E. Mooij and C. J. P. M. Harmans, New J. Phys. **7**, 219 (2005).
- [7] J. E. Mooij and Yu. V. Nazarov, Nature Phys. **2**, 169 (2006).
- [8] H. P. Buchler, V. B. Geshkenbein and G. Blatter, Phys. Rev. Lett. **92**, 067007 (2004).
- [9] V. E. Manucharyan, N. A. Masluk, A. Kamal, J. Koch, L.I. Glazman, M. H. Devoret, arXiv: 1012.1928 (2010).
- [10] V. A. Kashurnikov, A. I. Podlivaev, N. V. Prokof'ev and B. V. Svistunov, Phys. Rev. B **53**, 13091 (1996).
- [11] S. Khlebnikov, Phys. Rev. Lett. **93**, 090403 (2004); S. Khlebnikov, Phys. Rev. A **71**, 013602 (2005).
- [12] S. Khlebnikov and L. P. Pryadko, Phys. Rev. Lett. **95**, 107007 (2005).
- [13] F. D. M. Haldane, Phys. Rev. Lett. **47**, 1840 (1981).
- [14] Here and in the following we utilize the imaginary time formalism, $t \rightarrow i\tau$.
- [15] J. M. Graybeal and M. R. Beasley, Phys. Rev. B **29**, 4167 (1984).
- [16] A. A. Abrikosov, L. P. Gorkov, I. E. Dzyaloshinski, *Methods of Quantum Field Theory in Statistical Physics* (Dover Publications, Inc., 1975).